

PA66, excellent impact resistance, super toughened, low temperature impact resistance (-40°C).

Properties	Typical Value	Units	Test Method
<b>Mechanical Properties</b>			
	dry / cond.		
Tensile Modulus, 1 mm/min	1800 / 700	MPa	ISO 527-1/-2
Tensile Stress at Yield, 50 mm/min	40 / 30	MPa	ISO 527-1/-2
Tensile Strain at Yield, 50 mm/min	4 / 35	%	ISO 527-1/-2
Nominal Tensile Strain at Break, 50 mm/min	25 / >50	%	ISO 527-1/-2
Flexural Modulus, 2 mm/min	1700 / 600	MPa	ISO 178
Flexural Strength, 2 mm/min	60 / 30	MPa	ISO 178
Charpy Notched Impact Strength, +23°C	75 / 110	KJ/m <sup>2</sup>	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	16 / 15	KJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal Properties</b>			
Melting Temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temperature of Deflection Under Load, 1.8 MPa	60	°C	ISO 75-1/-2
Temperature of Deflection Under Load, 0.45 MPa	125	°C	ISO 75-1/-2
Flame Resistant, 1.5 mm	HB	Class	UL 94
<b>Electrical Properties</b>			
	dry / cond.		
Relative Permittivity, 1 MHz	3.1 / 3.6	-	IEC 62631-2-1
Volume Resistivity	4E12 / 1E10	Ohm.m	IEC 62631-3-1
Surface Resistivity	1E13 / 1E12	Ohm	IEC 62631-3-2
<b>Physical Properties</b>			
Density	1.08	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage, 2.0 mm, Parallel / Normal	1.8 / 1.4	%	ISO 294-4
Humidity Absorption, 23°C / 50% RH	2.0	%	Sim. to ISO 62
<b>Injection Molding</b>			
Drying Temperature	80	°C	4 hours
Melt Temperature	260 - 290	°C	-
Mould Temperature	60 - 90	°C	-

Revised: 06/26/2024

Sogun<sup>®</sup> provided information about the product, whether data, recommendations or other information, is researched and trustworthy. Since there are many influencing factors in the production process, users are advised to conduct their own tests before production. The standard values are for reference only and should not be regarded as binding specifications.

Find more information or contact us at [www.sogun.com](http://www.sogun.com)