

Sogun® A3V0HST

Product Information

Nylon Excellent toughness, low temperature impact resistance and thermal stability, UL94 V-0.

Properties	Test Method	Unit	Value
Mechanical Properties			dry/cond.
Tensile modulus	ISO 527-1/-2	MPa	2800/1000
Yield stress	ISO 527-1/-2	MPa	60/35
Yield strain	ISO 527-1/-2	%	4/20
Flexural modulus	ISO 178	MPa	2000/800
Izod notched impact strength, +23°C	ISO 180/1A	KJ/m ²	15/20
Izod notched impact strength, -30°C	ISO 180/1A	KJ/m ²	10/12
Thermal Properties			
HDT 1.8MPa	ISO 75	°C	65
HDT 0.45MPa	ISO 75	°C	125
Flame resistant, 0.4mm	UL 94	Class	V-0
Electrical Properties			dry/cond.
Relative permittivity, 1MHz	IEC 62631-2-1	–	3.5/7
Volume resistivity	IEC 62631-3-1	Ohm.m	1E13/1E11
Surface resistivity	IEC 62631-3-2	Ohm	1E13/1E14
Other Properties			
Density	ISO 1183	g/cm ³	1.16
Humidity absorption, 2mm	Sim. to ISO 62	%	2.6 - 3.0
Molding shrinkage	ISO 2577	%	0.8
Processing			
Drying temperature	4hr	°C	80
Melt temperature	–	°C	260 - 280
Mould temperature	–	°C	60 - 80

03/2024

Sogun® provided information about the product, whether data, advice or other information, are researched and trustworthy. Since there are many influencing factors in the production process, it is recommended that users test themselves before production. Standard values are only symbolic and should not be construed as binding specifications.