

PBT, excellent strength, stiffness, high temperature resistance, dimensional stability, surface finish, non-halogenated, flame retardant.

| Properties                                     | Typical Value | Units             | Test Method    |
|------------------------------------------------|---------------|-------------------|----------------|
| <b>Mechanical Properties</b>                   |               |                   |                |
| Tensile Modulus, 1 mm/min                      | 9200          | MPa               | ISO 527-1/-2   |
| Tensile Stress at Break, 5 mm/min              | 125           | MPa               | ISO 527-1/-2   |
| Tensile Strain at Break, 5 mm/min              | 2.2           | %                 | ISO 527-1/-2   |
| Flexural Modulus, 2 mm/min                     | 8500          | MPa               | ISO 178        |
| Flexural Strength, 2 mm/min                    | 165           | MPa               | ISO 178        |
| Charpy Notched Impact Strength, +23°C          | 7             | KJ/m <sup>2</sup> | ISO 179/1eA    |
| Charpy Notched Impact Strength, -30°C          | 6             | KJ/m <sup>2</sup> | ISO 179/1eA    |
| <b>Thermal Properties</b>                      |               |                   |                |
| Temperature of Deflection Under Load, 1.8 MPa  | 200           | °C                | ISO 75-1/-2    |
| Temperature of Deflection Under Load, 0.45 MPa | 210           | °C                | ISO 75-1/-2    |
| Flame Resistant, 3.0 mm                        | V-0           | Class             | UL 94          |
| <b>Electrical Properties</b>                   |               |                   |                |
| Relative Permittivity, 1 MHz                   | 3.9           | -                 | IEC 60250      |
| Volume Resistivity                             | 1E14          | Ohm.m             | IEC 60093      |
| Surface Resistivity                            | 1E16          | Ohm               | IEC 60093      |
| <b>Physical Properties</b>                     |               |                   |                |
| Density                                        | 1.54          | g/cm <sup>3</sup> | ISO 1183       |
| Molding Shrinkage, 2.0 mm, Parallel / Normal   | 0.4 / 1.1     | %                 | ISO 294-4      |
| Humidity Absorption, 23°C / 50% RH             | 0.15          | %                 | Sim. to ISO 62 |
| <b>Injection Molding</b>                       |               |                   |                |
| Drying Temperature                             | 120           | °C                | 4 hours        |
| Melt Temperature                               | 240 - 270     | °C                | -              |
| Mould Temperature                              | 60 - 90       | °C                | -              |

Revised: 06/26/2024

Sogun® provided information about the product, whether data, recommendations or other information, is researched and trustworthy. Since there are many influencing factors in the production process, users are advised to conduct their own tests before production. The standard values are for reference only and should not be regarded as binding specifications.

Find more information or contact us at [www.sogun.com](http://www.sogun.com)